



**INDUSTRIAL FABRICS, INC.**  
*Since 1981*

**HEADQUARTERS**  
 510 O' Neal Lane  
 Baton Rouge, LA 70819

225-273-9600 (Phone)  
 225-273-0440 (Fax)  
 www.ind-fab.com (Web)

## Geotextile Product Description Sheet

### GT -131 Nonwoven Geotextile

GT-131 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. GT-131 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. GT-131 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D 5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	3.1 (105)
Grab Tensile	ASTM D 4632	lbs (kN)	80 (0.35)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	30 (0.13)
CBR Puncture Resistance	ASTM D 6241	lbs (kN)	175 (0.76)
Permittivity*	ASTM D 4491	sec <sup>-1</sup>	2.2
Water Flow*	ASTM D 4491	gpm/ft <sup>2</sup> (l/min/m <sup>2</sup> )	150 (6095)
AOS*	ASTM D 4751	US Sieve (mm)	50 (0.30)
UV Resistance	ASTM D 4355	%/hrs	70/500

PACKAGING	
Roll Dimensions (W x L) – ft	12.5/15 x 360
Square Yards Per Roll	500/600
Estimated Roll Weight – lbs	125/145

\* At the time of manufacturing. Handling may change these properties.

**Made in U.S.A.**

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Industrial Fabrics, Inc. assumes no liability in connection with the use of this information.